

# Technical Data Sheet

## Trihexyltetradecylphosphonium decanoate


Revision Date: 11/18/2013

Date Issued: 11/18/2013

### 1 IDENTIFICATION OF THE SUBSTANCE/PREPARATION AND THE COMPANY/UNDERTAKING

<b>Product name</b>	Trihexyltetradecylphosphonium decanoate
<b>Product code</b>	IN-0008
<b>CAS</b>	465527-65-5
<b>Supplier</b>	IoLiTec Ionic Liquids Technologies GmbH Salzstrasse 184 D – 74076 Heilbronn Germany
<b>Telephone</b>	+49 (0)7131-89839-0
<b>Fax</b>	+49 (0)7131-89839-109
<b>Emergency telephone</b>	+49 (0)179-5322578
<b>Email</b>	info@iolitec.de

### 2 COMPOSITION/INFORMATION ON INGREDIENTS

<b>Ingredient name</b>	Trihexyltetradecylphosphonium decanoate
<b>CAS No.</b>	465527-65-5
<b>Empirical Formula</b>	$C_{42}H_{87}O_2P$
<b>Structure</b>	
<b>Molecular weight</b>	655.11 g/mol
<b>Purity</b>	>95%

# Technical Data Sheet

## Trihexyltetradecylphosphonium decanoate

Revision Date: 11/18/2013

Date Issued: 11/18/2013

### 3 PROPERTIES

<b>Color</b>	Yellow to orange
<b>Physical state (25 °C)</b>	Liquid
<b>Melting point</b>	-43 °C
<b>Glass transition temperature</b>	not available
<b>Decomposition temperature</b>	not available
<b>Density (25 °C)</b>	0.888 g/cm <sup>3</sup>
<b>Viscosity (25 °C)</b>	318.9 mPa * s
<b>Heat capacity (20 °C)</b>	not available
<b>Conductivity (30 °C)</b>	not available
<b>Electrochemical stability window</b>	not available
<b>Anodic limit</b>	not available
<b>Cathodic limit</b>	not available

### 4 CO-SOLVENT MISCIBILITY

<b>Water</b>	not miscible
<b>Acetone</b>	not available
<b>Acetonitrile</b>	not available
<b>Isopropanol</b>	not available
<b>Toluene</b>	miscible
<b>Hexane</b>	miscible

# Technical Data Sheet

## Trihexyltetradecylphosphonium decanoate

Revision Date: 11/18/2013

Date Issued: 11/18/2013

### 5 ORDER INFORMATION

IN-0008-HP can be obtained in the following standard quantities:

Quantity	Price
25 g	Please enquire
50 g	Please enquire
100 g	Please enquire
250 g	Please enquire
500 g	Please enquire
1 kg	Please enquire
Bulk	Please enquire

Please send your order via email to [order@iolitec.de](mailto:order@iolitec.de) or fax +49 (0)7131 – 89839109.

### 6 OTHER INFORMATION

#### DISCLAIMER

THE ABOVE INFORMATION IS BELIEVED TO BE CORRECT BUT DOES NOT PURPOSED TO BE ALL INCLUSIVE AND SHALL BE USED ONLY AS A GUIDE. IOLITEC SHALL NOT BE HELD LIABLE FOR ANY DAMAGE RESULTING FROM HANDLING OR FROM CONTACT WITH THE ABOVE PRODUCT. THIS INFORMATION RELATES ONLY TO THE SPECIFIC MATERIAL DESIGNATED AND MAY NOT BE VALID FOR SUCH MATERIAL USED IN COMBINATION WITH ANY OTHER MATERIALS OR ANY PROCESS. IT IS THE USER'S RESPONSIBILITY TO SATISFY HIMSELF AS TO THE SUITABILITY OF SUCH INFORMATION FOR HIS OWN PARTICULAR USE.

IN NO WAY SHALL IOLITEC BE LIABLE FOR ANY CLAIMS, LOSSES OR DAMAGES OF ANY THIRD PARTY OR FOR THE LOST PROFITS OR ANY SPECIAL, INDIRECT, INCIDENTAL, CONSEQUENTIAL OR EXEMPLARY DAMAGES, HOWSOEVER ARISING, EVEN IF THE COMPANY HAS BEEN ADVISED OF THE POSSIBILITY OF SUCH DAMAGES.